

Water dispersed hydrocarbon resin/ bitumen blend curing compound

Uses

The Concure B90 formulation and blend of bitumen resins and hydrocarbons, enables it to not only cures concrete but it also acts as a primer coat for asphalt and bitumen overlays.

It is ideally suitable for bridge decks and road construction where a concrete curing compound and bitumen primer can be applied in one application.

Advantages

- Ideal primer coat for asphalt or bitumen overlays on concrete roads, bridges or parking decks
- Complies with Australian Standards AS3799 - achieves water retention of >90%
- Contains no wax
- Reduces plastic shrinkage
- Eliminates the need for curing by ponded water, damp hession or polythene sheeting
- Waterbased - no solvent odour; clean equipment in water

Description

Concure B90 is a blend of bitumen and hydrocarbon resins emulsified in water. The film formed by Concure B90 prevents excessive water evaporation, promotes efficient cement hydration, minimises shrinkage whilst increasing durability of the concrete.

Properties

Data quoted typical for this product, but does not constitute a specification.

Appearance:	Black bituminous liquid
Volume solids:	49% ± 1%
Viscosity:	0.22 Pascal seconds
Flashpoint:	84°C
Drying time	
Tack Free:	1 - 3 hours
Hard Dry:	4 - 8 hours
Trafficable:	24 hours
Application Temperature:	10°C - 35°C

Application

Apply Concure B90 to the concrete as soon as the bleed water has gone and the new concrete has hardened sufficiently so as not to be marked by the application process.

Apply Concure B90 undiluted at a rate of 1 litre per 5m²/L. Best applied by spray, however, may also be applied by brush, roller or broom.

If the concrete surface is required to be trafficable prior to having an overlay placed then sand or fine stone can be placed over the Concure B90 to increase the abrasion resistance of the coating.

Cleaning

Concure B90 should be removed from tools and equipment with water.

Limitations

Concure B90 is NOT a “tack coat”. Where required a “tack coat” should still be applied.

Supply

Concure B90 is supplied on a “made to order” basis

Concure B90 1000 litre: FC600805-1000L

Coverage

5m²/litre

Storage

Concure B90 has a shelf life of 12 months if kept in a dry store in the original, unopened packs.

If stored at high temperatures and/or high humidity conditions the shelf life may be reduced.

Important notice

A Safety Data Sheet (SDS) is available from the Fosroc website. Read the SDS and TDS carefully prior to use as application or performance data may change from time to time. In emergency, contact any Poisons Information Centre (phone 13 11 26 within Australia) or a doctor for advice.

Product disclaimer

This Technical Data Sheet (TDS) summarises our best knowledge of the product, including how to use and apply the product based on the information available at the time. You should read this TDS carefully and consider the information in the context of how the product will be used, including in conjunction with any other product and the type of surfaces to, and the manner in which, the product will be applied. Our responsibility for products sold is subject to our standard terms and conditions of sale. Parchem does not accept any liability either directly or indirectly for any losses suffered in connection with the use or application of the product whether or not in accordance with any advice, specification, recommendation or information given by it.