



Torch applied 5mm thick, reinforced elastoplastomeric polymer – bitumen bridge deck waterproofing membrane

Uses

Proofex Torchseal A900 membrane is characterised by a high resistance to puncture and is therefore particularly suitable for single layer waterproofing systems where high mechanical resistance is required, such as:

- Bridge decks and viaducts
- Road ways
- Car parks
- Foundations
- Earthquake-proof foundations
- Subways and tunnels

Advantages

- APP polymer modified -specifically selected for Australian conditions
- Handles ponding and permanently wet conditions
- No curing times. Instantly waterproof
- Uniform thickness – eliminating likelihood of uneven application possible with liquid applied membranes
- Excellent stability at both high and low temperatures
- Excellent durability and flexibility

Description

Proofex Torchseal A900 is manufactured by co-extrusion of an elastoplastomeric bitumen-polymer compound with a softening point of $\geq 150^{\circ}\text{C}$ and of a non-woven polyester reinforcement of continuous filament weighing $\geq 250\text{g}/\text{m}^2$ placed in the thickness of the membrane. This ensures a very strong membrane with notable ultimate elongation and an optimal resistance to puncture and piercing.

The top face of Proofex Torchseal A900 is finished with a textured polypropylene film which prevents sticking when the membrane is in storage.

The lower face of the membrane is manufactured with a sacrificial polyethylene film which prevents sticking when the membrane is in storage.

Properties

Thickness:	5mm ($\pm 5\%$)
Mass:	5kg/m ² ($\pm 10\%$)
Reinforcement:	250g/m ² non woven polyester fabric:
Flow resistance at elevated temperature (EN 1110):	$\geq 140^{\circ}\text{C}$
Flexibility at low temperature (EN 1109):	\leq minus 15°C
Tensile strength (EN 12311-1) N/50 mm:	longitudinal: 1000 ($\pm 20\%$) transverse: 950 ($\pm 20\%$)
Tensile elongation (EN12311-1):	longitudinal: 40% ($\pm 15\%$) transverse: 40% ($\pm 15\%$)
Dimensional stability (EN1107-1):	$\leq 0.5\%$
Dynamic puncture (EN12691):	$\geq 1200\text{mm}$
Resistance to tearing (EN 12310-1):	longitudinal: 250 N ($\pm 30\%$) transverse: 250 N ($\pm 30\%$)
External fire performance (EN13501/5):	F _{Roof}
Reaction to fire (EN 13501/1):	Class E (internal report)
Impermeability to water (EN1928 B method):	500 kPa

Application Instructions

Surface preparation

All surfaces receiving the Proofex Torchseal A900 membrane must be firm, dry, and free from contaminants and loose material. Surfaces must also be even and smooth, without any defects that could damage the membrane. Rough concrete must be "faired up" before commencing application. For small repairs, suitable material can be made by mixing two parts fine clean sand with one part GP cement, a small amount of water to dampen the mix then add Fosroc Nitoproof 210 to make a trowelable paste..

Priming

Fosroc Primer 24 should be applied to all the prepared surfaces prior to the application of the membrane and allowed to dry. The primer will take at least one hour to dry at temperatures 25°C and above. At lower temperatures allow additional drying time.

Fosroc Primer 24 should be applied at the rate of approximately $8\text{m}^2/\text{litre}$ ($0.13\text{litre}/\text{m}^2$) to the surface to which Proofex Torchseal A900 will be applied. The coverage rate for the primer will vary depending on the porosity of the surface being treated.

Primer may be applied by brush, roller or spray equipment, coverage must be uniform. Primed areas must be covered with the membrane on the same day.

Fosroc® Proofex® Torchseal® A900

Application

Planning the installation of the membrane is important to ensure joints occur in suitable locations.

Proofex Torchseal A900 membrane must be laid to allow side laps of 80 to 100mm and end laps of 120 to 150mm. Application of the membrane is by torch bonding using a suitable gas torch. During the application of the gas flame the sacrificial polythene film will melt away.

Beginning at the lowest point of the deck area and working in the direction of the slope towards the highest point. The first roll of membrane is unrolled completely and aligned, remaining rolls should be unrolled approx. halfway in order to properly align the side lap and ensure the required 120 to 150mm end lap is maintained.

Starting at the low point in the deck apply heat by the gas torch to the outer surface of the rolled portion of membrane while un-rolling, move the flame from side to side while unrolling the membrane by slightly pressing it onto the underlying surface.

Avoid shifting the roll while unrolling. Follow the edge of the deck or the lap line. In order to have a smooth and even seal at the joint, apply the flame to the bleed out and the trowel simultaneously and spread the melted compound evenly to seal the joint.

Proceed torching the remaining membrane as described above, working your way to the highest point on the deck always maintaining the 100mm side lap and 150mm end lap.

On completion of the membrane installation all exposed perimeter edges must be mechanically fixed or terminated under a flashing.

Protection

Application of the road asphalt may be applied directly to the completed membrane, the tarmacadam acts as one body with the waterproofing membrane: therefore the laying temperature must be high and the tarmacadam compacted immediately by a roller.

Maintenance

No special requirements necessary. Any damage identified during normal inspections should be repaired or replaced as appropriate.

Important notice

A Safety Data Sheet (SDS) is available from the Fosroc website. Read the SDS and TDS carefully prior to use as application or performance data may change from time to time. In emergency, contact any Poisons Information Centre (phone 13 11 26 within Australia) or a doctor for advice.

Product disclaimer

This Technical Data Sheet (TDS) summarises our best knowledge of the product, including how to use and apply the product based on the information available at the time. You should read this TDS carefully and consider the information in the context of how the product will be used, including in conjunction with any other product and the type of surfaces to, and the manner in which, the product will be applied. Our responsibility for products sold is subject to our standard terms and conditions of sale. Parchem does not accept any liability either directly or indirectly for any losses suffered in connection with the use or application of the product whether or not in accordance with any advice, specification, recommendation or information given by it.

Limitations

New concrete substrates should be allowed to cure for a minimum of 28 days prior to the installation.

Supply

Proofex Torchseal A900 is supplied in 1m wide x 10m rolls

Proofex Torchseal A900:	FC007018-UNIT
--------------------------------	---------------

Fosroc Primer 24:	4 litre:	FC020500-4L
--------------------------	----------	-------------

Fosroc Primer 24:	20 litre:	FC020500-20L
--------------------------	-----------	--------------

Coverage

Proofex Torchseal A900:	Approx. 9m ² / 10m roll allowing for overlaps
--------------------------------	--

Fosroc Primer 24:	6 - 8m ² /litre
--------------------------	----------------------------

Note: no allowance has been made for wastage.

Storage

Store in cool, dry conditions ie. not exceeding 30°C. Rolls must be stored on end and must NOT be stored lying down.