Email: producttesting@awgc.com.au



FINAL REPORT

Internet: www.awgc.com.au

Report ID: 361681

Report Information

Submitting Organisation: 00109358 : Parchem Construction Supplies Pty Ltd

Account: 130335 : Parchem Construction Supplies Ptv Ltd

AWQC Reference: 130335-2022-CSR-4: Prod Test: Fosroc Renderoc LA55 Plus

Project Reference: PT-5142

Product Designation: Fosroc Renderoc LA55 Plus

Composition of Product : Cement Based Concrete Repair Mortar.

Product Manufacturer: Parchem Construction Supplies Pty Ltd., Wyong, NSW, AUSTRALIA.

Use of Product: In-Line/Cement Based Concrete Repair Flowable Mortar.

Sample Selection: As provided by the submitting organisation.

Testing Requested: AS/NZS 4020:2018 TESTING OF PRODUCTS FOR USE IN CONTACT WITH DRINKING

WATER

Product Type: Composite

Samples: Samples were prepared and controlled as described in Appendix A of AS/NZS 4020:2018

(Incorporating Amendment No.1)

Extracts: Extracts were prepared as described in Appendix/Clause C, D, E, F, G, H, 6.8.

Project Completion Date: 08-May-2023

Project Comment: Product sample received 19-Oct-2022, testing commenced 31-Jan-2023.

PLEASE NOTE THAT THIS REPORT SHALL NOT BE REPRODUCED EXCEPT IN FULL


THE RESULTS STATED IN THIS REPORT RELATE TO THE SAMPLE OF THE PRODUCT SUBMITTED FOR TESTING TO ASNZS 4020:2018. ANY CHANGES IN THE MATERIAL FORMULATION, PROCESS OF MANUFACTURE, THE METHOD OF APPLICATION, OR THE SURFACE AREA-TO-VOLUME RATIO IN THE END USE, COULD AFFECT THE SUITABILITY OF THE PRODUCT FOR USE IN CONTACT WITH DRINKING WATER







- 1. Uncertainty of Measurement is reported with a coverage factor of 2 providing approximately 95% confidence interval
- 2. Where a result is required to meet compliance limits the associated measurement uncertainty must be considered. Measurement uncertainty is available at





FINAL REPORT

Report ID:

Internet: www.awgc.com.au

Summary of Results

361681

APPENDIX/CLAUSE	RESULTS
C - Taste	Passed at an exposure of 15000 mm² per Litre.
D - Appearance	Passed at an exposure of 15000 mm² per Litre.
E - Growth of Aquatic Micro-organisms	Passed at an exposure of 15000 mm² per Litre.
F — Cytotoxic Activity	Passed at an exposure of 15000 mm² per Litre.
G - Mutagenic Activity	Passed at an exposure of 15000 mm² per Litre.
H - Metals	Passed at an exposure of 15000 mm² per Litre.
6.8 — Organic Compounds	Passed at an exposure of 15000 mm² per Litre.

Test Methods

Test(s) in Appendix	AWQC Test Method	NATA Accredited
С	T0320-01	Y
D	TO029-01 & TO018-01	Y
Е	TO014-03	Y
F	TM-001	Y
G	TM-002	Y
Н	TIC-006	Y

Organic Test Methods

Test(s) in Clause	Test Method	NATA Accredited
Clause 6.8	TMZ-M36	Υ
	EP239	Υ
	EP132-LL	Υ
	EP075C	Υ
	EP075ASIM	Υ





1. Uncertainty of Measurement is reported with a coverage factor of 2 providing approximately 95% confidence interval

2. Where a result is required to meet compliance limits the associated measurement uncertainty must be considered. Measurement uncertainty is available at

PO Box 1751 250 Victoria Square Adelaide SA 5001 Adelaide SA 5000 Tel: 1300 653 366 Fax: 1300 883 171 AWQC

Email: producttesting@awgc.com.au

Internet: www.awqc.com.au

FINAL REPORT

Report ID: 361681

Laboratory Information

Laboratory	NATA accreditation ID
Product Testing	1115
Australian Laboratory Services Pty Ltd - New South Wales	825,992
Inorganic Chemistry - Physical	1115
Protozoology	1115
Organic Chemistry	1115
Inorganic Chemistry - Metals	1115
Inorganic Chemistry - Waste Water	1115

Summary Comment:

The compound was applied (to glass slides) and cured for 7 days at 20° C prior to testing (ratio of 2000g powder to 230 mL of water. Ten sequential soakings performed to obtain a pH < 9.0. In accordance with section A8 (Cementitious Products).





- 1. Uncertainty of Measurement is reported with a coverage factor of 2 providing approximately 95% confidence interval
- 2. Where a result is required to meet compliance limits the associated measurement uncertainty must be considered. Measurement uncertainty is available at
- measurement-uncertainty



Internet: www.awqc.com.au Email: producttesting@awqc.com.au

FINAL REPORT

Report ID: 361681

CLAUSE 6.2 Taste

Sample Description The sample consisted of two coated panels (each coated to one side) with dimensions 75

mm x 100 mm and providing a total surface area of approximately 15000 mm²/L. Extracts

were prepared using 1000 mL volumes of pre-conditoning water(Al 12.6).

Extraction Temperature 20°C ± 2°C.

Test Method Taste (Appendix C)

Test Information

Scaling Factor Not applicable.

Results Not detected (sample and controls).

Evaluation The product passed the requirements of clause 6.2 when tested at an exposure of 15000 mm

² per Litre.

Number of Samples 2.

Test Comment Not applicable.

Peter Christopoulos
APPROVED SIGNATORY



Corporate Accreditation No.1115 Chemical and Biological Testing Accredited for compliance with ISO/IEC 17025 - Testing



Notes

- 1. Uncertainty of Measurement is reported with a coverage factor of 2 providing approximately 95% confidence interval
- 2. Where a result is required to meet compliance limits the associated measurement uncertainty must be considered. Measurement uncertainty is available at

AWQC

Internet: www.awqc.com.au Email: producttesting@awqc.com.au

FINAL REPORT

Report ID: 361681

CLAUSE 6.3 Appearance

Sample Description The sample consisted of two coated panels (each coated to one side) with dimensions 75

mm x 100 mm and providing a total surface area of approximately 15000 mm²/L. Extracts

were prepared using 1000 mL volumes of pre-conditoning water(Al 12.6).

Extraction Temperature $20^{\circ}\text{C} \pm 2^{\circ}\text{C}$.

Test Method Appearance (Appendix D)

Scaling Factor Not applicable.

Results

	Test (- Blank)	Maximum Allowed	<u>Units</u>
Colour	<1	5	HU
Turbidity	<0.1	0.5	NTU

Evaluation The product passed the requirements of clause 6.3 when tested at an exposure of 15000 mm

² per Litre.

Number of Samples 1.

Test Comment Not applicable.

Andrew Ford
APPROVED SIGNATORY



Corporate Accreditation No.1115 Chemical and Biological Testing Accredited for compliance with ISO/IEC 17025 - Testing



- . 1. Uncertainty of Measurement is reported with a coverage factor of 2 providing approximately 95% confidence interval
- 2. Where a result is required to meet compliance limits the associated measurement uncertainty must be considered. Measurement uncertainty is available at
- https://www.awqc.com.au/our-services/Water-quality-testing-and-analysis/measurement-uncertainty>

AWQC

Internet: www.awqc.com.au Email: producttesting@awqc.com.au

FINAL REPORT

Report ID: 361681

CLAUSE 6.4 Growth of Aquatic Micro-organisms

Sample Description The sample consisted of two coated panels (each coated to one side) with dimensions 75

mm x 100 mm and providing a total surface area of approximately 15000 mm²/L. Extracts

were prepared using 1000 mL volumes of test water.

Test Method Growth of Aquatic Micro-organisms (Appendix E)

Inoculum The volume of the inoculum was 100 mL

Scaling Factor Not applicable.

Results

Mean Dissolved Oxygen Control 7.3 mg/L

Mean Dissolved Oxygen Difference Positive Reference 5.4 mg/L

Negative Reference 0.1 mg/L

Test 0.10 mg/L

Evaluation The product passed the requirements of clause 6.4 when tested at an exposure of 15000 mm

² per Litre.

Number of Samples 1.

Test Comment Not applicable.

Thuy Diep
APPROVED SIGNATORY



Corporate Accreditation No.1115 Chemical and Biological Testing Accredited for compliance with ISO/IEC 17025 - Testing



Notes

- 1. Uncertainty of Measurement is reported with a coverage factor of 2 providing approximately 95% confidence interval
- 2. Where a result is required to meet compliance limits the associated measurement uncertainty must be considered. Measurement uncertainty is available at

AWQC

Internet: www.awqc.com.au Email: producttesting@awqc.com.au

FINAL REPORT

Report ID: 361681

CLAUSE 6.5 Cytotoxic Activity

Sample Description The sample consisted of two coated panels (each coated to one side) with dimensions 75

mm x 100 mm and providing a total surface area of approximately 15000 mm²/L. Extracts

were prepared using 1000 mL volumes of pre-conditoning water(Al 12.6).

Extraction Temperature $20^{\circ}\text{C} \pm 2^{\circ}\text{C}$.

Test Method Cytotoxic Activity (Appendix F)

Scaling Factor Not applicable.

Results 24 HR Non-cytotoxic response, healthy cell morphology with <30% cell death

48 HR Non-cytotoxic response, healthy cell morphology with <30% cell death

72 HR Non-cytotoxic response, healthy cell morphology with <30% cell death

Blank Control Results Blank; non-cytotoxic response, healthy cell morphology with <30% cell death

Positive Control Results Positive control; Cytotoxic response, unhealthy cell morphology with >70% cell death

The test extracts and blank extracts were used to prepare nutrient growth medium and subsequently used to grow a cell line (ATCC Number CCL 81) in the analysis. In addition

zinc sulphate (0.4 mmol) was used for the positive control in the analysis.

Evaluation The product passed the requirements of clause 6.5 when tested at an exposure of 15000 mm

² per Litre.

Number of Samples 1.

Test Comment Not applicable.

Mira Maric APPROVED SIGNATORY



Corporate Accreditation No.1115 Chemical and Biological Testing Accredited for compliance with ISO/IEC 17025 - Testing



- 1. Uncertainty of Measurement is reported with a coverage factor of 2 providing approximately 95% confidence interval
- 2. Where a result is required to meet compliance limits the associated measurement uncertainty must be considered. Measurement uncertainty is available at

AWQC

Internet: www.awqc.com.au Email: producttesting@awqc.com.au

FINAL REPORT

Report ID: 361681

CLAUSE 6.6 Mutagenic Activity

Sample Description The sample consisted of two coated panels (each coated to one side) with dimensions 75

mm x 100 mm and providing a total surface area of approximately 15000 mm²/L. Extracts

were prepared using 1000 mL volumes of pre-conditoning water(Al 12.6).

Extraction Temperature 20°C ± 2°C.

Test Method Mutagenic Activity (Appendix G)

Scaling Factor Not applicable.

Results

Bacteria Strain Number of Revertants per Plate

Salmonella typhimurium TA98 Mean ± Standard deviation	S9 -	Blank 26, 28, 33 29.0 ± 3.6	Sample Extract 34, 29, 30 31.0 ± 2.6	Positive Controls 3804, 3762, 3967 3844.3 ± 108.3	<u>NPD (</u> 20μg)
Mean ± Standard deviation	+	32, 29, 35 32.0 ± 3.0	44, 42, 37 41.0 ± 3.6	3630, 2936, 2332 2966.0 ± 649.5	<u>2-AF (</u> 20μg)
Salmonella typhimurium TA102 Mean ± Standard deviation	-	379, 370, 376 375.0 ± 4.6	413, 407, 388 402.7 ± 13.1	1962, 1997, 2138 2032.3 ± 93.2	<u>Mitomycin C(</u> 10μg)
Mean ± Standard deviation	+	412, 440, 438 430.0 ± 15.6	443, 452, 444 446.3 ± 4.9	1795, 1574, 1707 1692.0 ± 111.3	

The differences in the mean number of revertants between the blank and test extracts do not exceed two standard deviations; accordingly, there is no evidence of a mutagenic response.

Comments S9 was used as the metabolic activator. NPD (4-nitro-o-phenylenediamine) and Mitomycin

C are specific positive controls for strains TA98 - and TA102 (- and +) respectively, while 2-AF (2-aminofluorene) when used in conjunction with S9 is a positive control for TA98+.

Evaluation The product passed the requirements of clause 6.6 when tested at an exposure of 15000 mm

² per Litre.

Number of Samples 1.

Test Comment Not applicable.

Peter Christopoulos APPROVED SIGNATORY



Corporate Accreditation No.1115 Chemical and Biological Testing Accredited for compliance with ISO/IEC 17025 - Testing



- . 1. Uncertainty of Measurement is reported with a coverage factor of 2 providing approximately 95% confidence interval
- 2. Where a result is required to meet compliance limits the associated measurement uncertainty must be considered. Measurement uncertainty is available at
- https://www.awqc.com.au/our-services/Water-quality-testing-and-analysis/measurement-uncertainty>

Email: producttesting@awqc.com.au



FINAL REPORT

Report ID: 361681

Internet: www.awgc.com.au

CLAUSE 6.7 Metals

Sample Description The sample consisted of two coated panels (each coated to one side) with dimensions 75

mm x 100 mm and providing a total surface area of approximately 15000 mm²/L. Extracts

were prepared using 1000 mL volumes of pre-conditoning water(Al 12.6).

Extraction Temperature 20°C ± 2°C.

Test Method Metals (Appendix H)

Scaling Factor Not applicable.

Method of Analysis Concentration of the metals described in Table 2 of the AS/NZS 4020:2018 are determined

as follows:

Aluminium, Antimony, Arsenic, Barium, Boron, Cadmium, Chromium, Copper, Iron, Lead, Manganese, Mercury, Molybdenum, Nickel, Selenium and Silver by Inductively Coupled

Plasma Mass Spectrometry.

Results	Limit of Reporting mg/L	Blank mg/L	Test 1 mg/L	Test 2 mg/L	Max Allowed mg/L
Final Extract					
Aluminium	0.001	0.044	0.049	0.042	0.2
Antimony	0.0003	< 0.0003	< 0.0003	< 0.0003	0.003
Arsenic	0.00006	0.00040	0.00044	0.00043	0.01
Barium	0.0003	0.0285	0.0270	0.0267	0.7
Boron	0.020	<0.020	0.107	0.211	1.4
Cadmium	0.0001	<0.0001	< 0.0001	< 0.0001	0.002
Chromium	0.0001	0.0004	< 0.0001	< 0.0001	0.05
Copper	0.0001	0.1811	0.1494	0.1440	2.0
Iron	0.0005	0.0076	0.0058	0.0074	0.3
Lead	0.0001	0.0006	0.0007	0.0006	0.01
Manganese	0.0001	0.0008	0.0008	0.0009	0.1
Mercury	0.00003	<0.00003	<0.00003	< 0.00003	0.001
Molybdenum	0.0001	0.0003	0.0004	0.0004	0.05
Nickel	0.0002	0.0018	0.0018	0.0017	0.02
Selenium	0.0001	<0.0001	<0.0001	0.0001	0.01
Silver	0.00002	<0.00002	< 0.00002	<0.00002	0.1

Evaluation The product passed the requirements of clause 6.7 when tested at an exposure of 42000 mm

² per Litre.

Number of Samples 1.

Test Comment Not applicable.

Dzung Bui APPROVED SIGNATORY



Corporate Accreditation No.1115 Chemical and Biological Testing Accredited for compliance with ISO/IEC 17025 - Testing



Notes

- 1. Uncertainty of Measurement is reported with a coverage factor of 2 providing approximately 95% confidence interval
- 2. Where a result is required to meet compliance limits the associated measurement uncertainty must be considered. Measurement uncertainty is available at

Email: producttesting@awgc.com.au Internet: www.awgc.com.au

FINAL REPORT

361681 Report ID:

CLAUSE 6.8 Organic Compounds

Sample Description The sample consisted of two coated panels (each coated to one side) with dimensions 75 mm

x 100 mm and providing a total surface area of approximately 15000 mm²/L. Extracts were

prepared using 1000 mL volumes of pre-conditoning water(Al 12.6).

Extraction Temperature 20°C ± 2°C.

Test Method Organic Compounds (Clause 6.8). The maximum allowed (Max Allowed) values are taken from

the Australian Drinking Water Guidelines and Drinking-water Standards for New Zealand. Please

note, some reported compounds have no guideline value.

Not applicable. **Scaling Factor**

Results

Organic Compound

Nitrosamines	Blank	Test	Max Allowed
	μg/L	μg/L	
!External Lab Report No.	ES2304640	ES2304640	
1-Nitrosopiperidine (NPip)	<0.003	<0.003	
1-Nitrosopyrrolidine (NPyr)	<0.01	<0.01	
Nitrosomorpholine (NMor)	<0.003	<0.003	
N-Nitrosodiethylamine (NDEA)	<0.01	<0.01	
N-Nitrosodimethylamine (NDMA)	<0.003	<0.003	0.1 µg/L
N-Nitrosodi-n-propylamine (NDPA)	<0.003	<0.003	
N-Nitrosomethylethylamine (NMEA)	< 0.003	< 0.003	

C

Organic Compound			
Phenols	Blank	Test	Max Allowed
	μg/L	μg/L	
!External Lab Report No.	ES2304640	ES2304640	
2 4 5-trichlorophenol	<1.0	<1.0	
2 4 6-trichlorophenol	<1.0	<1.0	20 μg/L
2 4-dichlorophenol	<1.0	<1.0	200 μg/L
2 4-dimethylphenol	<1.0	<1.0	
2 6-dichlorophenol	<1.0	<1.0	
2-chlorophenol	<1.0	<1.0	300 μg/L
2-nitrophenol	<1.0	<1.0	
4-chloro-3-methylphenol	<1.0	<1.0	
m+p cresol	<2.0	<2.0	
o-cresol	<1.0	<1.0	
pentachlorophenol	<2.0	<2.0	9 μg/L
phenol	<1.0	<1.0	





- $1. \ Uncertainty \ of \ Measurement \ is \ reported \ with \ a \ coverage \ factor \ of \ 2 \ providing \ approximately \ 95\% \\$ confidence interval
- 2. Where a result is required to meet compliance limits the associated measurement uncertainty must be considered. Measurement uncertainty is available at
- https://www.awqc.com.au/our-services/Water-quality-testing-and-analysis/measurement-uncertainty



Internet: www.awgc.com.au Email: producttesting@awqc.com.au

FINAL REPORT

Report ID: 361681

Organic Co	mpound
------------	--------

Phthalate Esters	Blank μg/L	Test μg/L	Max Allowed
!External Lab Report No.	ES2304640	ES2304640	
Bis(2-ethylhexyl) phthalate	<10	<10	10 μg/L
Butyl benzyl phthalate	<2	<2	
Di(2-ethylhexyl) adipate	<2	<2	
Diethyl phthalate	<2	<2	
Dimethyl phthalate	<2	<2	
Di-n-butyl phthalate	<2	<2	
Di-n-octyl phthalate	<2	<2	

0

Organia Compound			
Organic Compound Polycyclic Aromatic Hydrocarbons	Blank	Test	Max Allowed
oryoyone Aremade Trydrocarbone	μg/L	μg/L	Wax / Wowca
!External Lab Report No.	ES2304640	ES2304640	
Acenaphthene	<0.02	<0.02	
Acenaphthylene	<0.02	<0.02	
Anthracene	<0.02	<0.02	
Benzo(a)anthracene	<0.02	<0.02	
Benzo(a)pyrene	<0.005	<0.005	0.01 µg/L
Benzo(a)pyrene TEQ	<0.005	<0.005	
Benzo(b+j)fluoranthene	<0.02	<0.02	
Benzo(ghi)perylene	<0.02	<0.02	
Benzo(k)fluoranthene	<0.02	<0.02	
Chrysene	<0.02	<0.02	
Dibenzo(a-h)anthracene	<0.02	<0.02	
Fluoranthene	<0.02	<0.02	
Fluorene	<0.02	<0.02	
Indeno(123-cd)pyrene	<0.02	<0.02	
Naphthalene	<0.02	<0.02	
PAH - Total	<0.005	<0.005	
Phenanthrene	<0.02	<0.02	
Pyrene	<0.02	<0.02	





1. Uncertainty of Measurement is reported with a coverage factor of 2 providing approximately 95% confidence interval

2. Where a result is required to meet compliance limits the associated measurement uncertainty must be considered. Measurement uncertainty is available at

 $\underline{\verb§|https://www.awqc.com.au/our-services/Water-quality-testing-and-analysis/measurement-uncertainty>}$



Internet: www.awqc.com.au Email: producttesting@awqc.com.au

FINAL REPORT

Report ID: 361681

Organic Compound

Organic Compound			
Volatile Organic Compounds GCMS	Blank	Test	Max Allowed
	μg/L	μg/L	
1 1 1 2-Tetrachloroethane	<1	<1	
1 1 1-Trichloroethane	<1	<1	
1 1 2 2-Tetrachloroethane	<1	<1	
1 1 2-Trichloroethane	<1	<1	
1 1-Dichloropropene	<1	<1	
1 2 3-Trichlorobenzene	<1	<1	
1 2 3-Trichloropropane	<1	<1	
1 2 4-Trichlorobenzene	<1	<1	
1 2 4-Trimethylbenzene	<1	<1	
1 2-Dibromo-3-chloropropane	<1	<1	1 μg/L
1 2-Dibromoethane	<1	<1	1 μg/L
1 2-Dichlorobenzene	<1	<1	1500 µg/L
1 2-Dichloroethane	<1	<1	3 μg/L
1 2-Dichloropropane	<1	<1	
1 3 5-Trimethylbenzene	<1	<1	
1 3-Dichlorobenzene	<1	<1	
1 3-Dichloropropane	<1	<1	
1 4-Dichlorobenzene	<1	<1	40 µg/L
1,1-Dichloroethane	<1	<1	
1,1-Dichloroethene	<1	<1	30 μg/L
2,2-Dichloropropane	<1	<1	
2-Chlorotoluene	<1	<1	
4-Chlorotoluene	<1	<1	
4-Isopropyltoluene	<1	<1	
Benzene	<1	<1	1 μg/L
Bromobenzene	<1	<1	
Bromochloromethane	<1	<1	
Bromodichloromethane	50	48	60 μg/L
Bromoform	6	6	100 µg/L
Bromomethane	<4	<4	
Carbon tetrachloride	<1	<1	3 μg/L
Chlorobenzene	<1	<1	300 μg/L
Chloroethane	<4	<4	
Chloroform	46	44	400 μg/L
Chloromethane	<4	<4	
cis-1 3-Dichloropropene	<1	<1	
cis-1,2-Dichloroethene	<1	<1	"
Dibromochloromethane	37	36	150 μg/L
Dibromomethane	<1	<1	
Dichlorodifluoromethane	<1	<1	
Dichloromethane	<4	<4	4 μg/L
Ethylbenzene	<1	<1	300 μg/L
Hexachlorobutadiene	<0.7	<0.7	0.7 μg/L
Isopropylbenzene	<1	<1	
m+p-Xylenes - Total	<2	<2	



Corporate Accreditation No.1115 Chemical and Biological Testing Accredited for compliance with ISO/IEC 17025 - Testing



- Uncertainty of Measurement is reported with a coverage factor of 2 providing approximately 95% confidence interval
- 2. Where a result is required to meet compliance limits the associated measurement uncertainty must be
 - considered. Measurement uncertainty is available at https://www.awqc.com.au/our-services/Water-quality-testing-and-analysis/measurement-uncertainty>



Internet: www.awqc.com.au Email: producttesting@awqc.com.au

FINAL REPORT

Report ID: 361681

Organic Compound

Volatile Organic Compounds GCMS	Blank	Test	Max Allowed
	μg/L	μg/L	
Naphthalene	<1	<1	
n-Butylbenzene	<1	<1	
n-Propylbenzene	<1	<1	
o-Xylene	<1	<1	
sec-Butylbenzene	<1	<1	
Styrene	<1	<1	30 μg/L
tert-Butylbenzene	<1	<1	
Tetrachloroethene	<1	<1	50 μg/L
Toluene	<1	<1	800 μg/L
Total 1 2-dichloroethene	<2	<2	60 µg/L
Total 1 3-dichloropropene	<2	<2	20 μg/L
Total Trichlorobenzene	<2	<2	30 μg/L
Total Xylene	<3	<3	600 μg/L
trans-1 3-Dichloropropene	<1	<1	
trans-1,2-Dichloroethene	<1	<1	
Trichloroethene	<1	<1	
Trichlorofluoromethane	<1	<1	
Trihalomethanes - Total	139	134	250 μg/L
Vinyl chloride	<0.3	<0.3	0.3 µg/L

Evaluation The product passed the requirements of clause 6.8 when tested at an exposure of 15000 mm²

per Litre.

Number of Samples

1.

Test Comment

The AWQC is not NATA accredited for the following tests: Nitrosamines, Phenols, Phthalate Esters and Polycyclic Aromatic Hydrocarbons. These tests are subcontracted to testing facilities that are NATA accredited for these analyses.

Qiong Huang

APPROVED SIGNATORY



Corporate Accreditation No.1115 Chemical and Biological Testing Accredited for compliance with ISO/IEC 17025 - Testing



- 1. Uncertainty of Measurement is reported with a coverage factor of 2 providing approximately 95% confidence interval
- 2. Where a result is required to meet compliance limits the associated measurement uncertainty must be considered. Measurement uncertainty is available at
- https://www.awqc.com.au/our-services/Water-quality-testing-and-analysis/measurement-uncertainty>